

## Statement of Verification

BREG EN EPD No.: 000129

Issue 08

This is to verify that the

### Environmental Product Declaration

provided by:

Diler Demir Celik Endustri ve Ticaret A.S.  
(member of UK CARES)

is in accordance with the requirements of:

EN 15804:2012+A2:2019

and

BRE Global Scheme Document SD207

This declaration is for:

Carbon Steel Reinforcing Bar (secondary production route - scrap)



### Company Address

Diler Demir Celik Endustri ve Ticaret A.S.  
Dilovasi Organize Sanayi Bolgesi  
1. Kisim, Dicle Cd. No: 30  
Dilovasi  
Kocaeli 41455  
Turkey




Signed for BRE Global Ltd

Emma Baker  
Operator

26 February 2025  
Date of this Issue

16 December 2019  
Date of First Issue

25 February 2028  
Expiry Date



This Statement of Verification is issued subject to terms and conditions (for details visit [www.greenbooklive.com/terms](http://www.greenbooklive.com/terms).  
To check the validity of this statement of verification please, visit [www.greenbooklive.com/check](http://www.greenbooklive.com/check) or contact us.  
BRE Global Ltd., Garston, Watford WD25 9XX.  
T: +44 (0)333 321 8811 F: +44 (0)1923 664603 E: [Enquiries@breglobal.com](mailto:Enquiries@breglobal.com)



## Environmental Product Declaration

EPD Number: 000129

### General Information

EPD Programme Operator	Applicable Product Category Rules
BRE Global Watford, Herts WD25 9XX United Kingdom	BRE Global Product Category Rules (PCR) for Type III EPD of Construction Products to EN 15804+A2. PN514 3.1
Commissioner of LCA study	LCA consultant/Tool
CARES Pembroke House 21 Pembroke Road Sevenoaks Kent, TN13 1XR UK <a href="http://www.carescertification.com">www.carescertification.com</a>	CARES EPD Tool SPHERA SOLUTIONS UK LIMITED The Innovation Centre Warwick Technology Park Gallows Hill, Warwick Warwickshire CV34 6UW <a href="http://www.sphera.com">www.sphera.com</a>
Declared/Functional Unit	Applicability/Coverage
1 tonne of carbon steel reinforcing bars manufactured by the secondary (scrap-based) production route as used within concrete structures for a commercial building.	Manufacturer-specific product.
EPD Type	Background database
Cradle to Gate with options	GaBi
Demonstration of Verification	
CEN standard EN 15804 serves as the core PCR <sup>a</sup>	
Independent verification of the declaration and data according to EN ISO 14025:2010 <input type="checkbox"/> Internal <input checked="" type="checkbox"/> External	
(Where appropriate <sup>b</sup> ) Third party verifier: Pat Hermon	
a: Product category rules b: Optional for business-to-business communication; mandatory for business-to-consumer communication (see EN ISO 14025:2010, 9.4)	
Comparability	
Environmental product declarations from different programmes may not be comparable if not compliant with EN 15804:2012+A2:2019. Comparability is further dependent on the specific product category rules, system boundaries and allocations, and background data sources. See Clause 5.3 of EN 15804:2012+A2:2019 for further guidance	

## Information modules covered

Product			Construction		Use stage							End-of-life				Benefits and loads beyond the system boundary
A1	A2	A3	A4	A5	Related to the building fabric					Related to the building		C1	C2	C3	C4	D
Raw materials supply	Transport	Manufacturing	Transport to site	Construction – Installation	Use	Maintenance	Repair	Replacement	Refurbishment	Operational energy use	Operational water use	Deconstruction demolition	Transport	Waste processing	Disposal	Reuse, Recovery and/or Recycling potential
<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>

Note: Ticks indicate the Information Modules declared.

## Manufacturing site

Diler Demir Celik Endustri ve Ticaret A.S. (member of UK CARES)

Dilovasi Organize Sanayi Bolgesi  
1. Kisim, Dicle Cd. No: 30  
Dilovasi  
Kocaeli 41455  
Turkey

## Construction Product:

### Product Description

Reinforcing steel bar (according to product standards listed in Sources of Additional Information) that is obtained from scrap, melted in an Electric Arc Furnace (EAF) followed by hot rolling.

The declared unit is 1 tonne of carbon steel reinforcing bars as used within concrete structures for a commercial building.

## Technical Information

Property	Value, Unit
Production route	EAF
Density	7850 kg/m <sup>3</sup>
Modulus of elasticity	200000 N/mm <sup>2</sup>
Weldability (Ceq)	max 0.50 %
Yield strength (as per BS 4449:2005+A3:2016)	min 500 N/mm <sup>2</sup> – max 650 N/mm <sup>2</sup>
Tensile strength (as per BS 4449:2005+A3:2016)	min 540 N/mm <sup>2</sup> (Tensile strength/Yield Strength $\geq$ 1.08)
Agt (% total elongation at maximum force as per BS 4449:2005+A3:2016)	min 5 %
Surface geometry (Relative rib area, $f_R$ as per BS 4449:2005+A3:2016)	min 0.040 for Bar Size >6mm & $\leq$ 12mm & min 0.056 for Bar size>12
Re-bend test (as per BS 4449:2005+A3:2016)	Pass
Fatigue test (as per BS 4449:2005+A3:2016)	Pass
Recycled content (as per ISO 14021:2016/Amd:2021)	97.1 %

\* Technical Information details are as per relevant product standards listed in References section.

## Main Product Contents

Material/Chemical Input	%
Fe	97
C, Mn, Si, V, Ni, Cu, Cr, Mo and others	3


## Manufacturing Process

Scrap metal is melted in an electric arc furnace to obtain liquid steel. This is then refined to remove impurities and alloying additions can be added to give the required properties.

Hot metal (molten steel) from the EAF is then cast into steel billets before being sent to the rolling mill where they are rolled and shaped to the required dimensions for the finished bars and coils of reinforcing steel.

The products are packed with steel wire or straps to bind the products, either of the steel ties and products do not include any biogenic materials.

## Process flow diagram



## Construction Installation

Processing and proper use of reinforcing steel products depends on the application and should be made in accordance with generally accepted practices, standards and manufacturing recommendations.

During transport and storage of reinforcing steel steel products the usual requirement for securing loads is to be observed.

## Use Information

The composition of the reinforcing steel products does not change during use.

Reinforcing steel products do not cause adverse health effects under normal conditions of use.

No risks to the environment and living organisms are known to result from the mechanical destruction of the reinforcing steel product itself.

## End of Life

Reinforcing steel products are not reused at end of life but can be recycled to the same (or higher/lower) quality of steel depending upon the metallurgy and processing of the recycling route.

It is a high value resource, so efforts are made to recycle steel scrap rather than disposing of it at EoL. A recycling rate of 92% is typical for reinforcing reinforcing steel products

## Life Cycle Assessment Calculation Rules

### Declared unit description

The declared unit is 1 tonne of carbon steel reinforcing bars manufactured by the secondary (scrap-based) production route as used within concrete structures for a commercial building (i.e. 1 tonne in use, accounting for losses during fabrication and installation, not 1 tonne as produced).

### System boundary

The system boundary of the EPD follows the modular design defined by EN 15804+A2. This is a cradle to gate – with all options EPD and thus covers all modules from A1 to C4 and includes module D as well.

Impacts and aspects related to losses/wastage (i.e. production, transport and waste processing and end-of-life stage of lost waste products and materials) are considered in the modules in which the losses/wastage occur.

Once steel scrap has been collected for recycling it is considered to have reached the end of waste state.

### Data sources, quality and allocation

Data Sources: Manufacturing data of the period 01/01/2021-31/12/2021 has been provided by Diler Demir Celik Endustri ve Ticaret A.S. (member of UK CARES).

Precise measuring or assumptions have been considered for primary data. Manufacturing data specific for rebar has been collected from recording of meters where applicable or justified assumptions has been made where metering systems were not applicable. Primary data was verified during audit conducted by CARES.

The selection of the background data for electricity generation is in line with the BRE Global PCR. Country or region specific power grid mixes are selected from LCA FE (GaBi) Dataset Documentation (Sphera 2023.1); thus, consumption grid mix of Turkiye has been selected to suit specific manufacturing location.

Data Quality: Data quality can be described as good. Background data are consistently sourced from the LCA FE (GaBi) Dataset Documentation (Sphera 2023.1). The primary data collection was thorough, considering all relevant flows and these data have been verified by CARES.

Data quality level and criteria of the UN Environment Global Guidance on LCA database development:

Geographical Representativeness	: Good
Technical Representativeness	: Very good
Time Representativeness	: Good

Allocation: EAF slag and mill scale are produced as co-products from the steel manufacturing process. Impacts are allocated between the steel, the slag and the mill scale based on economic value. The revenue generated from both mill scale and EAF slag are 0.10% and 0.27% respectively, and their total is less than 1% in relation to the product based on current market prices, these co-products are of definite value and are freely/readily traded in reality. For this reason, economic allocation has been applied to the processes where these co-products arise.

Production losses of steel during the production process are recycled in a closed loop offsetting the requirement for external scrap. Specific information on allocation within the background data is given in the LCA FE (GaBi) Dataset Documentation (Sphera 2023.1).

### Cut-off criteria

On the input side all flows entering the system and comprising more than 1% in total mass or contributing more than 1% to primary energy consumption are considered. All inputs used as well as all process-specific waste and process emissions were assessed. For this reason, material streams which were below 1% (by mass) were captured as well. In this manner the cut-off criteria according to the BRE guidelines are fulfilled.

The mass of steel wire or strand used for binding the product is less than 1 % of the total mass of the product.

## LCA Results

(MND = module not declared; MNR = module not relevant; INA = indicator not assessed; AGG = aggregated)

### Parameters describing environmental impacts

			GWP-total	GWP-fossil	GWP-biogenic	GWP-luluc	ODP	AP	EP-freshwater
			kg CO <sub>2</sub> eq	kg CO <sub>2</sub> eq	kg CO <sub>2</sub> eq	kg CO <sub>2</sub> eq	kg CFC11 eq	mol H <sup>+</sup> eq	kg (PO <sub>4</sub> ) <sup>3-</sup> eq
Product stage	Raw material supply	A1	274	274	2.24E-01	0.056	9.10E-07	1.26	2.77E-04
	Transport	A2	26.4	26.4	0.007	0.014	1.81E-12	0.867	1.09E-05
	Manufacturing	A3	549	548	0.926	0.051	2.22E-09	5.28	3.69E-04
	Total (of product stage)	A1-3	8.49E+02	8.48E+02	1.16	0.120	9.12E-07	7.41	6.57E-04
Construction process stage	Transport	A4	20.9	21	-0.292	0.191	1.81E-12	0.064	7.53E-05
	Construction	A5	96.4	96.2	0.062	0.062	9.07E-08	0.894	9.42E-05
Use stage	Use	B1	0	0	0	0	0	0	0
	Maintenance	B2	0	0	0	0	0	0	0
	Repair	B3	0	0	0	0	0	0	0
	Replacement	B4	0	0	0	0	0	0	0
	Refurbishment	B5	0	0	0	0	0	0	0
	Operational energy use	B6	0	0	0	0	0	0	0
	Operational water use	B7	0	0	0	0	0	0	0
%92 Recycling / %8 Landfill Scenario									
End of life	Deconstruction, demolition	C1	2.05	2.05	0.001	4.51E-05	6.29E-14	0.011	2.45E-07
	Transport	C2	47.1	47.3	-0.617	0.407	4.04E-12	0.235	1.61E-04
	Waste processing	C3	0	0	0	0	0	0	0
	Disposal	C4	1.17	1.2	-0.040	0.004	3.05E-12	0.009	2.42E-06
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	419	419	-0.819	0.174	-1.23E-09	0.944	3.10E-05
100% Lanfill Scenario									
End of life	Deconstruction, demolition	C1	2.05	2.05	0.001	4.51E-05	6.29E-14	0.011	2.45E-07
	Transport	C2	2.17	2.18	-0.030	0.020	1.88E-13	0.009	7.83E-06
	Waste processing	C3	0	0	0	0	0	0	0
	Disposal	C4	14.6	15	-0.499	0.047	3.82E-11	0.107	3.02E-05
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	2.49E+03	2.49E+03	-4.86	1.03	-7.30E-09	5.61	1.84E-04
100% Recycling Scenario									
End of life	Deconstruction, demolition	C1	2.05	2.05	0.001	4.51E-05	6.29E-14	0.011	2.45E-07
	Transport	C2	51.0	51.2	-0.668	0.440	4.37E-12	0.255	1.74E-04
	Waste processing	C3	0	0	0	0	0	0	0
	Disposal	C4	0	0	0	0	0	0	0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	239	239	-0.467	0.099	-7.02E-10	0.539	1.77E-05

GWP-total = Global warming potential, total;  
 GWP-fossil = Global warming potential, fossil;  
 GWP-biogenic = Global warming potential, biogenic;  
 GWP-luluc = Global warming potential, land use and land use change;

ODP = Depletion potential of the stratospheric ozone layer;  
 AP = Acidification potential, accumulated exceedance; and  
 EP-freshwater = Eutrophication potential, fraction of nutrients reaching freshwater end compartment



## LCA Results (continued)

Parameters describing environmental impacts			EP-marine	EP-terrestrial	POCP	ADP-mineral & metals	ADP-fossil	WDP	PM
			kg N eq	mol N eq	kg NMVOC eq	kg Sb eq	MJ, net calorific value	m <sup>3</sup> world eq	disease incidence
Product stage	Raw material supply	A1	0.205	1.93	0.540	2.76E-04	2.91E+03	10.4	1.47E-05
	Transport	A2	0.205	2.24	0.582	3.19E-07	320	0.058	1.50E-05
	Manufacturing	A3	0.399	4.45	1.33	2.69E-05	6.46E+03	327	4.83E-05
	Total (of product stage)	A1-3	0.809	8.62	2.45	3.03E-04	9.69E+03	3.37E+02	7.80E-05
Construction process stage	Transport	A4	0.029	0.329	0.058	1.33E-06	281	0.238	3.80E-07
	Construction	A5	0.099	1.09	0.298	3.12E-05	1.12E+03	42.5	9.12E-06
Use stage	Use	B1	0	0	0	0	0	0	0
	Maintenance	B2	0	0	0	0	0	0	0
	Repair	B3	0	0	0	0	0	0	0
	Replacement	B4	0	0	0	0	0	0	0
	Refurbishment	B5	0	0	0	0	0	0	0
	Operational energy use	B6	0	0	0	0	0	0	0
	Operational water use	B7	0	0	0	0	0	0	0
<b>%92 Recycling / %8 Landfill Scenario</b>									
End of life	Deconstruction, demolition	C1	0.004	0.044	0.011	1.25E-08	27.6	0.016	6.69E-08
	Transport	C2	0.113	1.26	0.235	2.86E-06	633	0.511	1.73E-06
	Waste processing	C3	0	0	0	0	0	0	0
	Disposal	C4	0.002	0.024	0.007	5.54E-08	16.0	0.132	1.05E-07
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	0.227	2.45	0.755	4.35E-06	3.10E+03	5.96	1.38E-05
<b>100% Lanfill Scenario</b>									
End of life	Deconstruction, demolition	C1	0.004	0.044	0.011	1.25E-08	27.6	0.016	6.69E-08
	Transport	C2	0.004	0.048	0.008	1.38E-07	29.2	0.025	4.68E-08
	Waste processing	C3	0	0	0	0	0	0	0
	Disposal	C4	0.028	0.303	0.083	6.92E-07	200	1.65	1.31E-06
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	1.35	14.6	4.48	2.58E-05	1.84E+04	35.4	8.19E-05
<b>100% Recycling Scenario</b>									
End of life	Deconstruction, demolition	C1	0.004	0.044	0.011	1.25E-08	27.6	0.016	6.69E-08
	Transport	C2	0.122	1.36	0.255	3.10E-06	685	0.553	1.88E-06
	Waste processing	C3	0	0	0	0	0	0	0
	Disposal	C4	0	0	0	0	0	0	0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	0.135	1.47	0.452	-5.05E-06	1.72E+03	-4.85	8.52E-06

EP-marine = Eutrophication potential, fraction of nutrients reaching marine end compartment;  
 EP-terrestrial = Eutrophication potential, accumulated exceedance;  
 POCP = Formation potential of tropospheric ozone;  
 ADP-mineral&metals = Abiotic depletion potential for non-fossil resources;

ADP-fossil = Depletion potential of the stratospheric ozone layer;  
 WDP = Water (user) deprivation potential, deprivation-weighted water consumption; and  
 PM = Particulate matter.



## LCA Results (continued)

Parameters describing environmental impacts							
			IRP	ETP-fw	HTP-c	HTP-nc	SQP
			kBq U <sup>235</sup> eq	CTUe	CTUh	CTUh	dimensionless
Product stage	Raw material supply	A1	4.11	2.77E-04	4.09E-08	2.88E-06	156
	Transport	A2	0.054	1.09E-05	4.15E-09	1.95E-07	9.27
	Manufacturing	A3	0.869	3.69E-04	8.77E-08	3.27E-06	572
	Total (of product stage)	A1-3	5.03	6.57E-04	1.33E-07	6.35E-06	7.37E+02
Construction process stage	Transport	A4	0.053	7.53E-05	3.98E-09	2.48E-07	117
	Construction	A5	0.592	9.42E-05	1.05E-08	7.53E-07	122
Use stage	Use	B1	0	0	0	0	0
	Maintenance	B2	0	0	0	0	0
	Repair	B3	0	0	0	0	0
	Replacement	B4	0	0	0	0	0
	Refurbishment	B5	0	0	0	0	0
	Operational energy use	B6	0	0	0	0	0
	Operational water use	B7	0	0	0	0	0
%92 Recycling / %8 Landfill Scenario							
End of life	Deconstruction, demolition	C1	5.08E-04	2.45E-07	6.18E-10	1.84E-08	0.043
	Transport	C2	0.117	1.61E-04	8.94E-09	5.50E-07	249
	Waste processing	C3	0	0	0	0	0
	Disposal	C4	0.021	2.42E-06	1.34E-09	1.48E-07	3.89
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	-6.09	3.10E-05	6.46E-07	2.50E-06	-292
100% Lanfill Scenario							
End of life	Deconstruction, demolition	C1	5.08E-04	2.45E-07	6.18E-10	1.84E-08	0.043
	Transport	C2	0.005	7.83E-06	4.14E-10	2.59E-08	12.2
	Waste processing	C3	0	0	0	0	0
	Disposal	C4	0.263	3.02E-05	1.68E-08	1.85E-06	48.6
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	-36.1	1.84E-04	3.83E-06	1.48E-05	-1.73E+03
100% Recycling Scenario							
End of life	Deconstruction, demolition	C1	5.08E-04	2.45E-07	6.18E-10	1.84E-08	0.043
	Transport	C2	0.127	1.74E-04	9.68E-09	5.96E-07	270
	Waste processing	C3	0	0	0	0	0
	Disposal	C4	0	0	0	0	0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	-3.47	1.77E-05	3.68E-07	1.43E-06	-167

IRP = Potential human exposure efficiency relative to U235;  
ETP-fw = Potential comparative toxic unit for ecosystems;  
HTP-c = Potential comparative toxic unit for humans;

HTP-nc = Potential comparative toxic unit for humans; and  
SQP = Potential soil quality index.

## LCA Results (continued)

Parameters describing resource use, primary energy								
			PERE	PERM	PERT	PENRE	PENRM	PENRT
			MJ	MJ	MJ	MJ	MJ	MJ
Product stage	Raw material supply	A1	310	0	310	2.92E+03	0	2.92E+03
	Transport	A2	2.72	0	2.72	321	0	321
	Manufacturing	A3	2.73E+03	0	2.73E+03	6.46E+03	0	6.46E+03
	Total (of product stage)	A1-3	3.04E+03	0	3.04E+03	9.70E+03	0	9.70E+03
Construction process stage	Transport	A4	19.9	0	19.9	281	0	281
	Construction	A5	386	0	386	1.12E+03	0	1.12E+03
Use stage	Use	B1	0	0	0	0	0	0
	Maintenance	B2	0	0	0	0	0	0
	Repair	B3	0	0	0	0	0	0
	Replacement	B4	0	0	0	0	0	0
	Refurbishment	B5	0	0	0	0	0	0
	Operational energy use	B6	0	0	0	0	0	0
	Operational water use	B7	0	0	0	0	0	0
<b>%92 Recycling / %8 Landfill Scenario</b>								
End of life	Deconstruction, demolition	C1	0.049	0	0.049	27.6	0	27.6
	Transport	C2	42.4	0	42.4	634	0	634
	Waste processing	C3	0	0	0	0	0	0
	Disposal	C4	2.61	0	2.61	16.0	0	16.0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	-516	0	-516	3.14E+03	0	3.14E+03
<b>100% Landfill Scenario</b>								
End of life	Deconstruction, demolition	C1	0.049	0	0.049	27.6	0	27.6
	Transport	C2	2.07	0	2.07	29.3	0	29.3
	Waste processing	C3	0	0	0	0	0	0
	Disposal	C4	32.6	0	32.6	200	0	200
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	-3.06E+03	0	-3.06E+03	1.86E+04	0	1.86E+04
<b>100% Recycling Scenario</b>								
End of life	Deconstruction, demolition	C1	0.049	0	0.049	27.6	0	27.6
	Transport	C2	45.9	0	45.9	687	0	687
	Waste processing	C3	0	0	0	0	0	0
	Disposal	C4	0	0	0	0	0	0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	-294	0	-294	1.79E+03	0	1.79E+03

PERE = Use of renewable primary energy excluding renewable primary energy used as raw materials;  
 PERM = Use of renewable primary energy resources used as raw materials;  
 PERT = Total use of renewable primary energy resources;

PENRE = Use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials;  
 PENRM = Use of non-renewable primary energy resources used as raw materials;  
 PENRT = Total use of non-renewable primary energy resource

## LCA Results (continued)

Parameters describing resource use, secondary materials and fuels, use of water						
			SM	RSF	NRSF	FW
			kg	MJ net calorific value	MJ net calorific value	m <sup>3</sup>
Product stage	Raw material supply	A1	0	0	0	10.4
	Transport	A2	0	0	0	0.058
	Manufacturing	A3	-1.13E+03	0	0	327
	Total (of product stage)	A1-3	-1.13E+03	0	0	3.37E+02
Construction process stage	Transport	A4	0	0	0	0.238
	Construction	A5	0	0	0	42.5
Use stage	Use	B1	0	0	0	0
	Maintenance	B2	0	0	0	0
	Repair	B3	0	0	0	0
	Replacement	B4	0	0	0	0
	Refurbishment	B5	0	0	0	0
	Operational energy use	B6	0	0	0	0
	Operational water use	B7	0	0	0	0
<b>%92 Recycling / %8 Landfill Scenario</b>						
End of life	Deconstruction, demolition	C1	0	0	0	0.016
	Transport	C2	0	0	0	0.511
	Waste processing	C3	0	0	0	0
	Disposal	C4	0	0	0	0.132
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	207	0	0	5.96
<b>100% Landfill Scenario</b>						
End of life	Deconstruction, demolition	C1	0	0	0	0.016
	Transport	C2	0	0	0	0.025
	Waste processing	C3	0	0	0	0
	Disposal	C4	0	0	0	1.65
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	1.13E+03	0	0	35.4
<b>100% Recycling Scenario</b>						
End of life	Deconstruction, demolition	C1	0	0	0	0.016
	Transport	C2	0	0	0	0.553
	Waste processing	C3	0	0	0	0
	Disposal	C4	0	0	0	0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	127	0	0	3.40

SM = Use of secondary material;  
RSF = Use of renewable secondary fuels;

NRSF = Use of non-renewable secondary fuels;  
FW = Net use of fresh water

## LCA Results (continued)

Other environmental information describing waste categories					
			HWD	NHWD	RWD
			kg	kg	kg
Product stage	Raw material supply	A1	7.93E-08	5.07	0.038
	Transport	A2	1.02E-09	0.030	3.80E-04
	Manufacturing	A3	4.09E-07	77.1	0.011
	Total (of product stage)	A1-3	4.89E-07	82.2	0.049
Construction process stage	Transport	A4	1.04E-09	0.041	3.64E-04
	Construction	A5	5.07E-08	18.0	0.006
Use stage	Use	B1	0	0	0
	Maintenance	B2	0	0	0
	Repair	B3	0	0	0
	Replacement	B4	0	0	0
	Refurbishment	B5	0	0	0
	Operational energy use	B6	0	0	0
	Operational water use	B7	0	0	0
%92 Recycling / %8 Landfill Scenario					
End of life	Deconstruction, demolition	C1	1.57E-11	0.004	7.03E-06
	Transport	C2	2.30E-09	0.090	8.15E-04
	Waste processing	C3	0	0	0
	Disposal	C4	3.49E-10	80.1	1.82E-04
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	7.91E-09	6.22	-0.055
100% Landfill Scenario					
End of life	Deconstruction, demolition	C1	1.57E-11	0.004	7.03E-06
	Transport	C2	1.08E-10	0.004	3.78E-05
	Waste processing	C3	0	0	0
	Disposal	C4	4.36E-09	1.00E+03	0.002
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	4.69E-08	36.9	-0.327
100% Recycling Scenario					
End of life	Deconstruction, demolition	C1	1.57E-11	0.004	7.03E-06
	Transport	C2	2.49E-09	0.097	8.82E-04
	Waste processing	C3	0	0	0
	Disposal	C4	0	0	0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	4.51E-09	3.55	-0.031

HWD = Hazardous waste disposed;  
 NHWD = Non-hazardous waste disposed;  
 RWD = Radioactive waste disposed

## LCA Results (continued)

Other environmental information describing output flows – at end of life								
			CRU	MFR	MER	EE	Biogenic carbon (product)	Biogenic carbon (packaging)
			kg	kg	kg	MJ per energy carrier	kg C	kg C
Product stage	Raw material supply	A1	0	0	0	0	0	0
	Transport	A2	0	0	0	0	0	0
	Manufacturing	A3	0	0	0	0	0	0
	Total (of product stage)	A1-3	0	0	0	0	0	0
Construction process stage	Transport	A4	0	0	0	0	0	0
	Construction	A5	0	-18.8	0	0	0	0
Use stage	Use	B1	0	0	0	0	0	0
	Maintenance	B2	0	0	0	0	0	0
	Repair	B3	0	0	0	0	0	0
	Replacement	B4	0	0	0	0	0	0
	Refurbishment	B5	0	0	0	0	0	0
	Operational energy use	B6	0	0	0	0	0	0
	Operational water use	B7	0	0	0	0	0	0
<b>%92 Recycling / %8 Landfill Scenario</b>								
End of life	Deconstruction, demolition	C1	0	-920	0	0	0	0
	Transport	C2	0	0	0	0	0	0
	Waste processing	C3	0	0	0	0	0	0
	Disposal	C4	0	0	0	0	0	0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	0	0	0	0	0	0
<b>100% Landfill Scenario</b>								
End of life	Deconstruction, demolition	C1	0	0	0	0	0	0
	Transport	C2	0	0	0	0	0	0
	Waste processing	C3	0	0	0	0	0	0
	Disposal	C4	0	0	0	0	0	0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	0	0	0	0	0	0
<b>100% Recycling Scenario</b>								
End of life	Deconstruction, demolition	C1	0	-1.00E+03	0	0	0	0
	Transport	C2	0	0	0	0	0	0
	Waste processing	C3	0	0	0	0	0	0
	Disposal	C4	0	0	0	0	0	0
Potential benefits and loads beyond the system boundaries	Reuse, recovery, recycling potential	D	0	0	0	0	0	0

CRU = Components for reuse;  
MFR = Materials for recycling

MER = Materials for energy recovery;  
EE = Exported Energy

## Scenarios and additional technical information

Scenarios and additional technical information			
Scenario	Parameter	Units	Results
A4 – Transport to the building site	On leaving the steelworks the reinforcing steel products are transported to a fabricator where they are converted into constructional steel forms suitable for the installation site, then transported on to the construction site, including provision of all materials and products. Road transport distance for rolled steel to fabricators and road transport distance for steel construction forms to site are assumed to be 100 km and 250 km, respectively. Only the one-way distance is considered as it is assumed that the logistics companies will optimise their distribution and not return empty in modules beyond A3.		
	Truck trailer - Fuel	litre/km	1.56
	Distance	km	350
	Capacity utilisation (incl. empty returns)	%	85
	Bulk density of transported products	kg/m <sup>3</sup>	7850
A5 – Installation in the building	The fabrication process is a relatively simple unit process and accounts for the transformation of the rolled steel product into construction steel forms. The operations in this unit process are primarily cutting and welding. As such, other inputs to the process include electricity, thermal energy, and cutting gases. Other outputs of this process are steel scrap and wastewater (where applicable). Fabrication into structural steel products and installation in the building; including provision of all materials, products, and energy, as well as waste processing up to the end-of-waste state or disposal of final residues during the construction stage. Installation of the fabricated product into the building is assumed to result in 10% wastage (determined based on typical installation losses reported by the WRAP Net Waste Tool [WRAP 2017]). It is assumed that fabrication requires 15.34 kWh/tonne finished product, and that there is a 2% wastage associated with this process.		
	Ancillary materials for installation - Waste material from fabrication, losses per tonne of construction steel forms	%	2
	Energy Use - Energy per tonne required to fabricate construction steel forms	kWh	15.34
	Waste materials from installation wastage	%	10
B2 – Maintenance	No maintenance required		
B3 – Repair	No repair process required		
B4 – Replacement	No replacement considerations required		
B5 – Refurbishment	No refurbishment process required		
Reference service life	Reinforcing steel products are used in the main building structure so the reference service life will equal the lifetime of the building. The Concrete Society follows the definitions provided in BS EN 1990, which specifies “building structures and other common structures” as having a lifetime of 50 years ( <a href="https://www.concrete.org.uk/design-working-life">Design working life (concrete.org.uk)</a> ). On this basis, the RSL for this EPD is assumed to be 50 years.		
B6 – Use of energy; B7 – Use of water	No water or energy required during use stage related to the operation of the building		

### Scenarios and additional technical information

Scenario	Parameter	Units	Results
C1 to C4 End of life,	The end-of-life stage starts when the construction product is replaced, dismantled or deconstructed from the building or construction works and does not provide any further function. The recovered steel is transported for recycling while a small portion is assumed to be unrecoverable and remains in the rubble which is sent to landfill. 92% of the reinforcing steel is assumed to be recycled and 8% is sent to landfill [STEELCONSTRUCTION.INFO 2012]. Once steel scrap is generated through the deconstruction activities on the demolition site it is considered to have reached the “end of waste” state. No further processing is required so there are no impacts associated with this module. Hence no impacts are reported in module C3.		
	Waste for recycling - Recovered steel from crushed concrete	%	92
	Waste for energy recovery - Energy recovery is not considered for this study as most end of life steel scrap is recycled, while the remainder is landfilled	-	-
	Waste for final disposal - Unrecoverable steel lost in crushed concrete and sent to landfill	%	8
	Portion of energy assigned to rebar from energy required to demolish building, per tonne	MJ	24
	Transport to waste processing by Truck - Fuel consumption	litre/km	1.56
	Transport to waste processing by Truck – Distance	km	463
	Transport to waste processing by Truck – Capacity utilisation	%	85
	Transport to waste processing by Truck – Density of Product	kg/m <sup>3</sup>	7850
	Transport to waste processing by Container ship - Fuel consumption	litre/km	0.0041
	Transport to waste processing by Container ship - Distance	km	158
	Transport to waste processing by Container ship – Capacity utilisation	%	50
	Transport to waste processing by Container ship – Density of Product	kg/m <sup>3</sup>	7850
Module D	It is assumed that 92% of the steel used in the structure is recovered for recycling, while the remainder is landfilled. “Benefits and loads beyond the system boundary” (module D) accounts for the environmental benefits and loads resulting from net steel scrap that is used as raw material in the EAF and that is collected for recycling at end of life. The balance between total scrap arisings recycled from fabrication, installation and end of life and scrap consumed by the manufacturing process (internally sourced scrap is not included in this calculation). These benefits and loads are calculated by including the burdens of recycling and the benefit of avoided primary production.		
	This study is concerned with the secondary production route and more scrap is required as input to the system than is recovered at end of life. The net effect of this is that module D mainly models the burdens associated with the scrap input (secondary material) to the steelmaking process.		
	The resulting scrap credit/burden is calculated based on the global “value of scrap” approach (worldsteel 2017).		
	Recycled Content	kg	971
	Re-used Content	kg	0
	Recovered for recycling	kg	920
	Recovered for re-use	kg	0
	Recovered for energy	kg	0



## Summary, comments and additional information

### Interpretation

Scrap based reinforcing steel product of Diler Demir Celik Endustri ve Ticaret A.S. (member of CARES) is made via the EAF route. The bulk of the environmental impacts and primary energy demand is attributed to the manufacturing phase, covered by information modules A1-A3 of EN 15804+A2.

The interpretation of the results has been carried out considering the methodology- and data-related assumptions and limitations declared in the EPD. This interpretation section focuses on the environmental impact categories as well as the primary energy demand indicators only.

#### Global Warming Potential (GWP)

The majority of the life cycle GWP impact occurs in the production phase (A1-A3). A1-A3 impacts account for 83.52% overall life cycle impacts for this category. The most significant contributions to production phase impacts are: the upstream production of raw materials used in the steelmaking process, generation/supply of electricity and the production/use of fuels on site. Fabrication, installation and the end-of-life processes covered in C1-C4 make a minimal contribution to GWP. For overall climate change impacts, carbon dioxide emissions account for the majority of impacts with methane being the second most significant contributor.

#### Ozone Depletion Potential (ODP)

The majority of impacts are associated with the production phase (A1-3). Significant contributions to production phase impact come from the emission of ozone depleting substances during the upstream production of raw materials/pre-products as well as those arising from electricity production. Module D shows a very small credit even though scrap burdens are being assessed in this phase. This is explained because ODP emissions are linked to grid electricity production used.

#### Acidification Potential (AP)

Acidification potential is generally driven by the production of sulphur dioxide and nitrogen oxides through the combustion of fossil fuels, particularly coal and crude oil products. The majority of the lifecycle AP impact occurs in the production phase (A1-A3), similar to GWP. The major contributors to production phase AP impacts comes from energy resources used in the production of the raw materials and pre-products for the steelmaking process and from transportation. Fabrication, installation and the end-of-life processes classed under C1-C4 make minimal contributions.

#### Eutrophication Potential (EP)

Eutrophication is driven by nitrogen and phosphorus containing emissions and as with GWP and AP is often strongly linked with the use of fossil fuels. The major eutrophication impacts occur in the production phase (A1-A3). Significant contributions to production phase impact comes from the production of raw materials and transport. Fabrication, installation and the end-of-life processes classed under C1-C4 again make minimal contributions.

#### Photochemical Ozone Creation Potential (POCP)

POCP tends to be driven by emissions of carbon monoxide, nitrogen oxides (NO<sub>x</sub>), sulphur dioxide and NMVOCs. The production phase is the dominant phase of the lifecycle with regards to POCP impacts. Again, these are all emissions commonly associated with the combustion of fuels. Significant contributors to POCP are the upstream production of raw materials/pre-products and transport, directly linked to fossil fuel combustion. It should be noted that the impacts for steel recycling in module D is almost of the same magnitude as the production phase impacts.




Figure 1 - shows the relative contribution of each life cycle stage to different environmental indicators for the carbon steel reinforcing bars manufactured by the Direct Reduced Iron production route

## References

- BSI. Sustainability of construction works – Environmental product declarations – Core rules for the product category of construction products. BS EN 15804:2012+A2:2019. London, BSI, 2019.
- BSI. Environmental labels and declarations – Type III Environmental declarations – Principles and procedures. BS EN ISO 14025:2010 (exactly identical to ISO 14025:2006). London, BSI, 2010.
- BSI. Environmental management – Life cycle assessment – Principles and framework. BS EN ISO BS EN ISO 14040:2006+A1:2020. London, BSI, 2020.
- BSI. Environmental management – Life cycle assessment – requirements and guidelines. BS EN ISO 14044:2006+A2:2020. London, BSI, 2020.
- Demolition Energy Analysis of Office Building Structural Systems, Athena Sustainable Materials Institute, 1997
- The Concrete Society, [Design working life \(concrete.org.uk\)](https://www.concrete.org.uk)
- LCA FE (GaBi) Software System and Database for Life Cycle Engineering, Sphera Solution GmbH, Leinfelden-Echterdingen
- LCA FE (GaBi) Dataset Documentation for the LCA FE Software System and Database for Life Cycle Engineering, version 2023.1, Sphera Solution GmbH, Leinfelden-Echterdingen, [https://www.LCA FE \(GaBi\)-software.com/databases/LCA FE \(GaBi\)-databases/](https://www.LCA FE (GaBi)-software.com/databases/LCA FE (GaBi)-databases/)
- International Energy Agency, Energy Statistics 2013. <http://www.iea.org>
- Kreißig, J. und J. Kümmel (1999): Baustoff-Ökobilanzen. Wirkungsabschätzung und Auswertung in der Steine-Erden-Industrie. Hrsg. Bundesverband Baustoffe Steine + Erden e.V.
- U,S, Geological Survey, Mineral Commodity Summaries, Iron and Steel Slag, January 2014
- SteelConstruction.info; The recycling and reuse survey, 2012  
[http://www.steelconstruction.info/The\\_recycling\\_and\\_reuse\\_survey](http://www.steelconstruction.info/The_recycling_and_reuse_survey)
- Sustainability of construction works - Environmental product declarations - Methodology for selection and use of generic data; German version CEN/TR 15941
- REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC
- WRAP (2017). WRAP (Waste & Resources Action Programme) Net Waste Tool
- worldsteel Association - Life cycle inventory methodology report for steel products, 2017
- CARES SCS Sustainable Constructional Steel Scheme v9 – Operational assessment schedule - <https://www.carescertification.com/certified-companies/search> - Certificate number of conformance to SCS v9 at the time of LCA study – 1272.
- CARES SRC Steel for the Reinforcement of Concrete Scheme. Appendix 1 – Quality and operations assessment schedule for carbon steel bars for the reinforcement of concrete including inspection and testing requirements - <https://www.carescertification.com/certified-companies/search> - Certificate number of conformance to BS4449 at the time of LCA study – 011001

CARES SRC Steel for the Reinforcement of Concrete Scheme. Appendix 1-N - Quality and operations assessment schedule for carbon steel bars for the reinforcement of concrete for use in nuclear applications and other mega projects including inspection and testing requirements - <https://www.carescertification.com/certified-companies/search> - Certificate number of conformance to BS4449 at the time of LCA study – 170601

CARES SSRC Singapore Steel for the Reinforcement of Concrete Scheme - Appendix 1 Quality and operations assessment schedule for Singapore Standard (SS 560:2016) weldable reinforcing steel bars, coils and decoiled products for the reinforcement of concrete including inspection and testing requirements - <https://www.carescertification.com/certified-companies/search> - Certificate number of conformance to SS 560:2016 at the time of LCA study – 180601

CARES SRC Steel for the Reinforcement of Concrete Scheme. Appendix CP&AS 24 - Quality and operations assessment schedule for Hong Kong Standard (CS2:2012) Steel Reinforcing Bars for the Reinforcement of Concrete - <https://www.carescertification.com/certified-companies/search> - Certificate number of conformance to CS2:2012 at the time of LCA study – 190405

BS 4449:2005+A3:2016 Steel for the reinforcement of concrete. Weldable reinforcing steel. Bar, coil and decoiled product. Specification.

SS 560:2010 - Steel for the reinforcement of concrete – Weldable reinforcing steel – Bar, coil and decoiled product. BDS 9252:2007 - Steel for the reinforcement of concrete - Weldable reinforcing steel B500.

CS2:2012 - Steel Reinforcing Bars for the Reinforcement of Concrete

ASTM A615/A615M – 22 Standard Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement.

ASTM A706/A706M – 22 - Standard Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement.

ISO 6935-2:2019 - Steel for the reinforcement of concrete - Part 2: Ribbed bars.

EN 10080:2005 Steel for the reinforcement of concrete. Weldable reinforcing steel. General

DIN 488-2:2009 - Reinforcing steels - Reinforcing steel bars.

NF A35-080-1:2020 - Aciers pour béton armé - Aciers soudables - Partie 1 : barres et couronnes.

CAN/CSA G30.18-09:2012 Carbon steel bars for concrete reinforcement.

UNE 36068:2011 - Ribbed bars of weldable steel for the reinforcement of concrete.

UNE 36065:2011- Ribbed bars of weldable steel with special characteristics of ductility for the reinforcement of concrete.

NBN A 24-302:1986 Siderurgique produits. Reinforcing steels

TS 708:2016 - Steel for the reinforcement of concrete - Reinforcing steel.

BDS 9252:2007 - Steel for the reinforcement of concrete - Weldable reinforcing steel B500.

BDS 4758:2008 - Steel for reinforcement of concrete. Weldable reinforcing steels B235 and B420

AS/NZS 4671:2019 Steel for the reinforcement of concrete

MS 146:2014 – Steel for the reinforcement of concrete – Weldable reinforcing steel – Bar, coil and decoiled product - Specification (Fourth revision)

SI 4466-3:2013 - Steel for the reinforcement of concrete: Ribbed Bars.

ABNT NBR 7480:2007 - Steel for The Reinforcement of Concrete Structures – Specification.

GOST R 52544:2006 - Weldable deformed reinforcing rolled products of A500C and B500C classes for reinforcement of concrete constructions. Specifications.

SS 2-2:1999 (2020) - Steel for the reinforcement of concrete - Ribbed bars (steel grade 500)

NTP 341.031-2008 especificación normalizada para barras de acero con resaltes y lisas para hormigón (concreto) armado

NCh 204:2006 - Steel - Hot rolled bars for reinforced concrete

KS D3504:2011 - Steel Bars for Concrete Reinforcement

PNA 4 007:2009 - Steel Bars for Reinforcement of Concrete

SR 438-1:2012 – Steel products for concrete reinforcement. Part-1: Hot Rolled Structural Steel

NT 26-05:2004 - Production Details of Rebars For Tunisia

NA 8634:1997 - Steel for the Reinforcement of Concrete: Ribbed Bars

D.M:2008 - Steel for the Reinforcement of Concrete Bars of Grade (B450C)